

Product Specification

VF190+ Anti-Fouling Film Fill



C. E. Shepherd Company

Product Description

VF190+ is a vertical channel film fill with very low fouling potential and excellent thermal performance designed for installation in heavy industrial counterflow cooling towers. The fill packs are constructed from individual sheets of UV protected PVC formulated for cooling tower applications and in compliance with CTI-136. The fill packs will operate satisfactorily in continuous operating temperatures of 140°F or less.

The surface of the fill has an engineered microstructure to improve heat transfer. The individual sheets are strategically bonded together at “DEDICATED JOINTS” with a male/female connection and a destructive connection. The final assembly results in a staggered pattern of flutes to form a structurally sound honeycomb pattern.

This fill is suitable for applications where TSS levels are 100 ppm or less (500 ppm if bacterial activity is low), make-up is from uncontaminated sources, water treatment includes good to fair biological & scale control, there are minimal airborne contaminants and oils or greases in the system are limited to 5 ppm.



CES VF190+

Applicable Commercial Standards

Property	Test Method	Typical Values
Specific Gravity	ASTM-D792	1.41 ± 0.04
Tensile Strength (psi)	ASTM-D638	5500 min
Tensile Modulus (psi)	ASTM-D638	3.5 x 10 ⁶ min
Flexural Strength (psi)	ASTM-D790	10,000 min
Flexural Modulus	ASTM-D790	3.5 x 10 ⁶ min
Heat Distortion Temperature (°F)	ASTM-D648	162 min
Flammability 1	UL94 Vertical Burning	94V-0
Flammability 2	UL94 Horizontal Burning	94H-B
Flame Spread	ASTM-E84	25 or less

ASTM methods shown above are based on the Annual Book 1999 and have been modified to suit practical conditions.

For dimensions and/or physical properties different from those listed above or special requirements including weatherability, flammability, etc., contact CES for agreement on the specifications.

Statements and methods presented are based upon the best available information and practices known to CES. Because conditions of use may vary and are beyond our control, CES makes no warranty, expressed or implied, concerning the use of products. The user should undertake sufficient tests to determine the suitability for any intended use of the material. CES assumes no responsibilities for the use of information presented herein and hereby disclaims all liability in regard to such use. No statements are intended or should be construed as a recommendation to infringe any patent.

Product Dimensions

Description	Units	Value
Flute Height	Inches	0.75
Flute Width	Inches	2.00
Flute Corrugation Angle	Degrees	0.0
Surface Area	SF/CF	45
Contact Points /SF	#/CF	450
Module Depth	Inches	23.6
Module Width	Inches	12.0/24.0
Max Module Length	Inches	120.0
Sheet Thickness Before Forming	Mils	14.0/19.0
Sheet Thickness After Forming	Mils	10.0/15.0

Custom module sizes and sheet thickness can be tailored to customer specification. Contact CE Shepherd Co for details.

CE Shepherd Company L.P.

2221 Canada Dry Street | Houston, TX 77023
 713.924.4300 (Main) | 713.928.2559 (Fax)
 Email: coolingtowers@ceshepherd.com

